Kotex Polycarbonate



Grade: R-20E Post-consumer recycled grade

Colour: Natural High flow

Properties	Standards	Test conditions	Units	Typical values
Mechanical Properties				
Izod impact strength	ASTM D256	23°C V-notched 1/8"	J/m	620
			kgf•cm/cm	63
			ft•lbf/in	12
Tensile strength at break	ASTM D638		MPa	61
			kgf/cm ²	620
			lbf/in ²	8800
Tensile elongation at break	ASTM D638		%	100
Flexural strength	ASTM D790		MPa	84
			kgf/cm ²	860
			lbf/in ²	12200
Flexural modulus	ASTM D790		MPa	2100
			kgf/cm ²	21600
			lbf/in ²	306000
Thermal Properties				
Melt flow rate	ASTM D1238	300℃, 1.2kgf	g/10min	21
Heat deflection temperature	ASTM D648	18.6 kgf/cm ²	°C	126
			°F	259
Electrical Properties				
Dielectric breakdown strength	ASTM D149	1.6mm	kV/mm	20
Dielectrical constant	ASTM D150	10 ⁶ Hz		2.9
Dissipation factor	ASTM D150	$10^6 \mathrm{Hz}$		0.009
Arc resistance	ASTM D495		Sec.	110
Volume resistivity	ASTM D257		Ω•cm	10 ¹⁶
Optical Properties				
Light transmittance	ASTM D1003	3.0 mm	%	
Light refractive	ASTM D542			
Haze	ASTM D1003	3.0 mm	%	
Other Properties				
Specific gravity	ASTM D792			1.20
Water absorption	ASTM D570	24 hrs at 23°C water immersion	%	0.2
Mould shrinkage	ASTM D955		%	0.5~0.7
	UL94	1.6 mm		(Equivalent V-2)

To our best knowledge, the values contained herein are typical of uncoloured PC and given in good faith. They may be affected by colorants, other additives, the design of a mould/die, moulding techniques applied, the size and shape of a moulded article. In view of these factors, the properties do not relieve customers from carrying out their own investigations and tests. It is entirely the customer's responsibility to determine the suitability of material and grade used for their intended application. No warranty, express or implied is made nor is liability accepted in connection with any of the information provided. We reserve the right to make additions, deletions, or modifications to the information at any time without prior notification. Kotec Corporation (18.2.2023)