

Grade: RS-1350

Recycled grade

Colour: Black

GF 50% reinforced

Properties	Standards	Test conditions	Units	Typical values
Mechanical Properties				
Izod impact strength	ASTM D256	23°C V-notched 1/8"	J/m	108
			kgf•cm/cm	11
			ft•lbf/in	2
Tensile strength at break	ASTM D638	---	MPa	159
			kgf/cm ²	1620
			lbf/in ²	23000
Tensile elongation at break	ASTM D638	---	%	3
Flexural strength	ASTM D790	---	MPa	202
			kgf/cm ²	2060
			lbf/in ²	29300
Flexural modulus	ASTM D790	---	MPa	12200
			kgf/cm ²	124400
			lbf/in ²	1769000
Thermal Properties				
Melt flow rate	ASTM D1238	300°C, 5.0kgf	g/10min	30
Heat deflection temperature	ASTM D648	18.6 kgf/cm ²	°C	274
			°F	525
Electrical Properties				
Dielectric breakdown strength	ASTM D149	1.6mm	kV/mm	16
Dielectrical constant	ASTM D150	10 ⁶ Hz	---	4.0
Dissipation factor	ASTM D150	10 ⁶ Hz	---	—
Arc resistance	ASTM D495	---	Sec.	—
Volume resistivity	ASTM D257	---	Ω•cm	10 ¹⁶
Optical Properties				
Light transmittance	ASTM D1003	3 mm	%	—
Light refractive	ASTM D542	---	---	—
Haze	ASTM D1003	3 mm	%	—
Other Properties				
Specific gravity	ASTM D792	---	---	1.71
Water absorption	ASTM D570	24 hrs at 23°C water immersion	%	0.02
Mould shrinkage	ASTM D955	MD/TD	%	—
Flammability	UL94	1.5 mm	---	V-0(equivalent)

To our best knowledge, the values contained herein are typical of uncoloured PPS and given in good faith. They may be affected by colorants, other additives, the design of a mould/die, moulding techniques applied, the size and shape of a moulded article. In view of these factors, the properties do not relieve customers from carrying out their own investigations and tests. It is entirely the customer's responsibility to determine the suitability of material and grade used for their intended application. No warranty, express or implied is made nor is liability accepted in connection with any of the information provided. We reserve the right to make additions, deletions, or modifications to the information at any time without prior notification. Kotec Corporation (6.2.2023)